

We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

4,800

Open access books available

122,000

International authors and editors

135M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities



WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com



Spectroscopic Insights into the Nano-Bio Interface

Achyut J. Raghavendra, Wren Gregory,
Indushekhar Persaud, Jared M. Brown and
Ramakrishna Podila

Additional information is available at the end of the chapter

<http://dx.doi.org/10.5772/intechopen.69384>

Abstract

Engineered nanomaterials (ENMs) strongly interact with biomolecules due to their unique physicochemical properties. From the standpoint of nanotoxicity, it is imperative to achieve a comprehensive understanding of various nano-bio interactions to ultimately design benign ENMs that do not elicit adverse physiological responses. Spectroscopic tools are ideal for elucidating the underlying biophysical mechanisms of nano-bio interactions. In this chapter, we review spectroscopy techniques, such as Raman, infrared, circular dichroism (CD), and hyperspectral imaging, to illuminate the nano-bio interface. Particularly, we discuss the role of spectroscopic tools in gaining a fundamental understanding of the formation and influence of protein corona on ENM physiological responses.

Keywords: protein corona, spectroscopy, nano-bio interface, silver

1. Introduction

The advancement of nanotechnology over the past two decades has spurred the fields of health care, information technology, energy, homeland security, food safety, and transportation; and the global market for nanotechnology-related products reached more than \$200 billion in 2009 with a projected \$1 trillion per annum by 2015 (US Senate Committee, 2011) [1]. Despite this enormous global market, there remain several concerns regarding the impact of engineered nanomaterials (ENMs) on biological responses in living organisms and the environment at large [1–7]. A comprehensive knowledge of the ENM-biomolecular interactions is central to applications in nanomedicine, consumer goods, and other unintentional exposures. Currently, there are more than 40 nanopharmaceuticals in routine clinical use, and the patents and publications on

nanomedicine have been exponentially increasing [8]. Considering that nanomedicine efforts are a sudden convergence of contrasting scientific disciplines (e.g., materials science, bioengineering, pharmacology), the advancement and acceptance of nanotechnology rely heavily on a holistic interdisciplinary understanding of the impact of fundamental properties of ENMs (such as their morphology, size, defects, and chemical stability) on physiological and environmental systems.

Upon introduction into a biological system, ENMs rapidly associate a variety of macromolecules including proteins, peptides, amino acids, fatty acids, lipids, and other organic matter forming protein biocorona [9–11]. The formation of the corona is dictated not only by the physicochemical properties of the ENM but also by the composition of the physiological environment [12]. The addition of the corona on the surface of the ENM imparts a new distinctive interactive surface, which influences activity, deposition, clearance, and cytotoxicity [13–15]. The biocorona has also been shown to compromise the targeting capacity of functionalized ENMs and subsequently hinder delivery therapy [11, 16, 17]. In addition, the inconsistencies observed between *in vitro* and *in vivo* extrapolation of ENM toxicity are likely contributable to differences in ENM-biocorona formation [9, 18]. Spectroscopic tools are ideal for exploring the biological interactions of ENMs with proteins [19–21]. As discussed in this chapter, combining spectroscopic tools with traditional toxicological studies can provide unique insights into the nano-bio interface that could be used to ultimately design benign ENMs.

2. Spectroscopic insights into protein corona

2.1. Hyperspectral imaging

Gold and silver nanoparticles display a collective and resonant oscillation of surface electrons, known as plasmons, upon light excitation in the visible region (400–700 nm). The surface plasmon resonance is highly sensitive to both nanoparticles aggregation and the dielectric constant of the environment surrounding them. In a biological medium, the presence of protein corona around nanoparticles alters the SPR peak by modifying the dielectric constant [22]. Similarly, their cellular uptake could lead to aggregation, which is known to red shift the SPR peak [23]. Hyperspectral imaging is an excellent tool that combines microscopy and spectroscopy in real time by accumulating reflectance spectrum for each pixel in a micrograph. Thus, the state of nanoparticles and protein corona upon cellular uptake can be gleaned from the hyperspectral micrographs [24–26]. Recently, we explored the cellular uptake of silver nanoparticles (Ag NPs) with and without protein corona using hyperspectral imaging [23]. Our studies revealed intracellular modifications resulting from protein corona formation as shown in **Figure 1**. Changes in the microenvironment of AgNPs were evidently reflected in the shift of plasmon energies allowing us to differentiate between intra- and extra-cellular nanoparticles. Hyperspectral imaging presents an alternative to traditional electron microscopy methods for the identification of nanoparticles and protein corona inside the cell [27–30]. The exhaustive sample preparation needed for electron microscopy, such as encapsulation in a polymer followed by microtoming, often leads to artifacts. For example, the large agglomerates formed during the electron microscopy sample preparation are indistinguishable from agglomerates resulting from the loss of nanoparticles surface coating upon entering biological media.




Figure 1. (a) Hyperspectral-enhanced darkfield images of macrophages exposed to AgNPs and AgNPs with protein corona for 2 hours, at a concentration of 25 $\mu\text{g/mL}$. Macrophage nucleus appears blue in the images due to DAPI stain. (b) Differences in mean spectra for AgNPs with different sizes (20 and 110 nm) and coatings (PVP and citrate). Based on such shifts in plasmon energies, it is possible to study the uptake and modification of AgNPs using hyperspectral imaging.

2.2. Circular dichroism (CD) spectroscopy

ENM-protein complex formation poses concerns on potential denaturation of proteins, which can alter protein binding to receptors and induce inflammatory responses. Lysozyme, for example, adsorbed on gold nanoparticles (AuNPs) was observed to induce misfolded proteins which likely catalyze the formation of aggregates [31]. Similarly, fibrinogen was found to unfold on the surface of stabilized (negatively charged with polyacrylic acid) AuNPs and bind to integrin receptor (MAC-1) leading to inflammatory response [32]. Circular dichroism (CD) spectroscopy has been extensively used to study conformational changes in biomolecules [33–35]. CD studies on ENM protein corona can elucidate the changes in protein secondary structures ensuing from their adsorption to ENMs surface [36]. For example, apolipoprotein (ApoA-I) protein, which is known to be abundant in the protein corona of metal nanoparticles, exhibited secondary structural changes dependent on the surface coating (**Figure 2**). ApoA-I is the major lipoprotein component of high-density lipoprotein (HDL). It adopts a shape similar to a horseshoe of dimensions $12.5 \times 8 \times 4$ nm with high α -helix content [37–39]. The helices in ApoA-I are predicted to be amphipathic, with the hydrophobic (/hydrophilic) face mediating lipid (/aqueous) interactions. The thermodynamic drive to minimize the aqueous exposure of the hydrophobic residues is one of the major factors in ApoA-I adsorption on AgNPs [40, 41]. We studied the interactions between ApoA-I and 100-nm AgNPs with four different coatings, viz., citrate, polyvinylpyrrolidone (PVP), branched polyethylenimine (bPEI), and lipoic acid [42]. These coatings were chosen to provide both negative (citrate, PVP, lipoic acid) and positive charged surfaces (bPEI) with different affinities for AgNPs. While lipoic acid interacts strongly through Ag-S bonds, other coatings (citrate, PVP, bPEI) are considerably weaker. As shown in **Figure 2**, CD studies showed a significant decrease in α -helical content for all surface coatings with the complete disappearance of α -helices for AgNP-bPEI and AgNP-lipoic acid. From a physiological standpoint, we found a significant increase in the ability of ApoA-I-coated AgNP-bPEI and AgNP-lipoic acid to generate reactive oxygen species due to its unfolding. The conformational changes observed in CD can provide more information on ENM-protein corona complex and may be even used as a predictor for adverse immune responses.




Figure 2. (a) Circular dichroism (CD) spectra for ApoA-I incubated with AgNPs of different surface coatings (citrate, PVP, bPEI, and lipoic acid) show (b) marked decrease in α -helix content with corresponding increase in β -sheets and irregular structures. Spectra were analyzed using CAPITO (a CD Analysis & Plotting Tool), and secondary structure content was estimated. CD spectroscopy provides secondary and tertiary protein structure content estimation of biomolecules, which is critical for analyzing conformational changes during ENM-protein interactions.

2.3. Infrared spectroscopy

Unlike metal nanoparticles, carbon-based ENMs exhibit strong optical absorption $<240 \text{ nm}$ due to their π -electron system, which can interfere with protein CD spectra collected in $200\text{--}300 \text{ nm}$ range, precluding the use of CD to study nanocarbon-protein corona. Alternatively, we used ATR-FTIR (attenuated total internal reflection-Fourier transform infrared) spectroscopy to elucidate the adsorption-induced structural changes in proteins (bovine serum albumin or BSA and fibrinogen) on carbon ENMs such as multi-walled carbon nanotubes (MWNTs), graphene, and graphene oxide nanoribbons (GNRs and GONRs). The FTIR spectrum of proteins displays two main bands, Amide I ($1600\text{--}1700 \text{ cm}^{-1}$) and Amide II ($1500\text{--}1580 \text{ cm}^{-1}$), arising from the amide bonds that link the amino acids in proteins. While Amide I band is mainly associated with the C=O stretching vibration, Amide II band results primarily from bending vibrations of the N-H bond. Given that both the C=O and the N-H bonds are involved in the hydrogen bonding between the different peptide units, their spectral position and intensity can be used to determine the secondary structure content of a protein. For example, as shown in **Figure 3**, the α -helical content in BSA leads to strong adsorption of $\sim 1640\text{--}1660 \text{ cm}^{-1}$ (dashed lines), while the lower frequency component at $\sim 1620\text{--}1640 \text{ cm}^{-1}$ and the peak $\sim 1555 \text{ cm}^{-1}$ arise from β -sheets. Clearly, the rich secondary structure of BSA (particularly, the peak relating to α -helical content) significantly disappears upon its adsorption on to all carbon-based NMs, as expected from its low internal stability. Indeed, the changes in secondary structure are higher in the case of MWNTs (i.e., complete disappearance of secondary structure), suggesting that BSA unfolds much more, relative to GNRs and GONRs, in order to adhere to the tubular MWNTs. GNR and GONR retain BSA secondary structure to certain extent, as shown by the presence of $\sim 1555 \text{ cm}^{-1}$ for β -sheets. In the case of fibrinogen, the secondary structural changes are found to be higher for GONRs compared to MWNTs and GNRs plausibly due to the formation of hydrogen bonds. The α -helix peak was found to partially disappear for fibrinogen adsorbed on MWNTs and GNRs. Lastly, the




Figure 3. (a–c) Snapshots of MD simulations showing BSA on SWNT, GNR, and GONR 10 ns after adsorption. (d–f) show the top view. The adsorption is accompanied by disruption of α -helices into random peptide chains.




Figure 4. (a) FTIR spectra for native BSA and BSA adsorbed on MWNTs, GNRs, and GONRs show that the CNMs significantly affected the secondary structures of the proteins. The absorption peak for α -helix in native BSA, in the range from 1640 to 1660 cm^{-1} (indicated by the vertical dashed lines), showed a significant reduction (disappeared for MWNTs) for all CNMs, suggesting that the secondary structure of BSA adsorbed on CNMs was less compact. (b) In the case of fibrinogen, the loss of secondary structure was highest for GONRs possibly due to the formation of hydrogen bonds. While both MWNTs and GNRs exhibited a loss of α -helical content, the appearance of new peak $\sim 1500 \text{ cm}^{-1}$ (corresponding to random motifs) in GNRs suggested a lesser degree of relaxation for fibrinogen, compared to MWNTs.

structural changes for fibrinogen on GNRs seemed to be less pronounced than MWNTs possibly due to its shape. It could be rationalized that fibrinogen must unfold more to adhere to MWNTs due to their higher curvature than GNRs. To further understand NM-BSA interactions, we also performed large-scale molecular dynamics (MD) simulations of BSA-MWNT, GNR/GONR-water systems (detailed in [43]). As shown in **Figure 3**, we observed that proteins undergo conformational changes after initial contact (in accordance with our experimental observations, discussed in **Figure 4**), leading to some protein regions collapsing on to the ENM surface rather than gradually spreading from the initial region of contact.

3. Probing electronic interactions at the nano-bio interface

Charge transfer is known to play an important role in several many physiological processes including blood clotting, vitamin absorption, and oxidative stress [44–46]. Differences in electro-negativity between proteins and the ENM surface may induce charge transfer which, along with other perturbations in the media (e.g., pH, thermodynamic fluctuations), plays a critical role in protein denaturation, protein-protein interactions, and alterations to the cellular and extracellular redox status. Such interactions are not necessarily specific, with conformational changes possibly resulting in newly exposed charged regions and hydrophobic domains attracting or repelling other surrounding proteins or nanostructures. Electronic properties of ENMs, including their band structure and density of states, have been shown to regulate protein adsorption dynamics via charge transfer, which are evident as shifts in absorption and emission spectra [47, 48].

3.1. Charge transfer during corona formation

The chemisorption of proteins on bulk material surfaces has been known to occur through charge transfer processes. For example, the aromatic amino acids present in BSA (tryptophan, phenylalanine, histidine, and tyrosine) could interact with the unhybridized p_z orbitals of the carbon-based ENMs, via providing a weak acceptor level in the electronic density of states (DOS) to allow partial charge transfer. It may be expected that a surface facilitating higher charge transfer at the nanoscale may lead to stronger surface-protein interactions and a subsequent increase in protein adsorption. Spectroscopic and electrochemical techniques such as micro-Raman, CD, and cyclic voltammetry can be used to analyze and elucidate the influence of charge transfer on protein affinity for ENMs and the alterations in secondary and tertiary structures that occur with adsorption. Among variety of ENMs, nanocarbons possess strong affinity for proteins through hydrophobic and aromatic π - π stacking interactions [49]. Previously, we elucidated the charge transfer interactions between nanocarbons and proteins using micro-Raman spectroscopy. Our results show that strong interaction of proteins (albumin and fibrinogen) with nanocarbons is strongly influenced by charge transfer between them, inducing protein unfolding which enhances conformational entropy and higher protein adsorption. For instance, the UV-visible absorption spectrum of single-wall carbon nanotubes (SWNTs) coated with BSA were found to blue shift significantly, while BSA-coated graphene sheets (both exfoliated and synthesized via chemical vapor deposition) exhibited no such changes [50]. Additionally, micro-Raman spectroscopy revealed alterations

in the structure of the G-band (or graphitic band) of BSA-coated SWNTs. The G-band, which is highly sensitive to charge transfer, was found to be upshifted with a Breit-Wigner-Fano line-shape resulting from electron transfer between BSA and SWNTs. No changes were observed for graphene upon protein coating, indicating that ENMs-BSA charge transfer is unique to SWNTs. Concomitantly, FTIR spectroscopy revealed subsequent conformational changes in BSA (**Figure 4**) in the form of uncompacting of α -helices, suggesting hard corona formation on SWNTs as opposed to graphene. These results insinuate that disruption in electrostatics due to ENM-protein charge transfer leads to the breaking of peripheral H-bonds in the α -helices and permanent denaturation of BSA on SWNTs [50, 51].

3.2. Two-dimensional (2D) materials

Unique properties of two-dimensional (2D) nanomaterials, including boron nitride (BN), graphene, and graphene oxide, relate to their electronic interactions with biomolecules. The 2D structure of these ENMs gives rise to π -electron clouds which can interact strongly with other π -electrons in proteins or amino acids [52]. While we predominantly focused on proteins, it is important to note that individual amino acid interactions with ENMs are equally significant indicators of corona formation and cytotoxicity modeling. In particular, aromatic amino acids offer π -electrons similar to 2D ENMs, and therefore exhibit this strong affinity for certain 2D materials through this π - π electron stacking. We studied interactions between aromatic amino acids (tryptophan, tyrosine, and phenylalanine) and 2D nanomaterials (graphene, graphene oxide or GO, and BN) using micro-Raman and photoluminescence (PL) spectroscopy combined with electrochemical characterization. Perturbation in the electronic structure was evident through changes in Raman spectra as shown in **Figure 5**, and results were quantified using CV measurements (**Figure 6**). Downshift in characteristic G and 2D bands in the spectra




Figure 5. Raman spectra of graphene (Gr)-amino acid complexes show significant shifts in carbon characteristic (a) G band and (b) 2D band indicating charge transfer between amino acid and graphene. Solid line indicates fits to experimental data. Panel b shows deconvoluted peaks of 2D band. Downshift in G and 2D bands for graphene-tyrosine complex indicates upshift in fermi level (E_f) induced by electron transfer from tyrosine.




Figure 6. (a) Cyclic voltammetry (CV) curves for graphene and tryptophan show appearance of new peak $\sim 0.6\text{--}0.8$ V indicating irreversible charge transfer. (b) Percent change in reactive oxygen species (ROS) by macrophages when exposed different 2D materials like graphene (Gr), boron nitride (BN), and graphene oxide (GO) to amino acid complexes (tyrosine, tryptophan, and phenylalanine). Sensitivity to charge transfer makes electrochemical impedance spectroscopy a valuable tool in probing nano-bio interactions.

indicated upshift in Fermi level induced from electron transfer from the amino acid. In CV characterization, the application of gate voltage on the working electrode (i.e., ENMs) modulates its electronic energy levels, which when above (/below) the LUMO (/HOMO) levels of the protein can result in a charge transfer. While reversible charge transfer in redox couples appears as two peaks in the CV curve (one for oxidation and the other for reduction), only a single peak is often observed for irreversible charge transfer. The irreversibility of these charge transfer between 2D ENMs and amino acids was confirmed with appearance of new peak ($\sim 0.6\text{--}0.8$ V) in our CV curves. Further findings suggested variance in π -electron cloud structure in graphene and BN determined electron stacking orientation and associated amino acid affinity, while functional groups mediated affinity through H-bonding in GO. As shown in **Figure 6b**, indeed adsorption of amino acids on 2D materials significantly alters their ability to generate reactive oxygen species [52].

4. Conclusions

Understanding the biological interactions of ENMs with a biocorona and its influence on cellular uptake, generation of reactive oxygen species, and cytotoxicity is critical to implement the safe use of ENMs. Spectroscopic tools offer critical insights into the nano-bio interface by providing information regarding the protein adsorption affinity, the influence of charge transfer, and protein unfolding on ENMs. Hyperspectral imaging is an excellent complementary technique to electron microscopy. The changes in the micro-environment of ENMs are reflected in their hyperspectra allowing one to identify intra-cellular ENMs. Circular dichroism and infrared spectroscopy are sensitive to the changes in protein structure, while Raman and cyclic voltammetry provide information about the charge transfer between ENMs and proteins. A comprehensive characterization of ENM-protein corona with spectroscopic tools

is necessary for establishing relationships between ENM physicochemical properties and their biological responses.

Author details

Achyut J. Raghavendra^{1,3}, Wren Gregory^{1,3}, Indushekhar Persaud⁴, Jared M. Brown⁴ and Ramakrishna Podila^{1,2,3*}

*Address all correspondence to: rpodila@g.clemson.edu

1 Department of Physics and Astronomy, Clemson Nanomaterials Center, Clemson University, Clemson, SC, USA

2 Center for Optical Materials Science and Engineering Technologies, Clemson University, Clemson, SC, USA

3 Laboratory of Nano-bio Physics, Clemson University, Clemson, SC, USA

4 Department of Pharmaceutical Sciences, the University of Colorado Anschutz Medical Campus, Aurora, CO, USA

References

- [1] Wiesner MR, Lowry GV, Alvarez P, Dionysiou D, Biswas P. Assessing the risks of manufactured nanomaterials. *Environmental Science and Technology*. 2006;**40**:4336-4345
- [2] Dror I, Yaron B, Berkowitz B. Abiotic soil changes induced by engineered nanomaterials: A critical review. *Journal of Contaminant Hydrology*. 2015;**181**:3-16
- [3] Colvin V. The potential environmental impact of engineered nanomaterials. *Nature Biotechnology*. 2003;**21**(10):1166-1170
- [4] Farré M, Gajda-Schranz K, Kantiani L, Barceló D. Ecotoxicity and analysis of nanomaterials in the aquatic environment. *Analytical and Bioanalytical Chemistry*. 2009;**393**(1): 81-95
- [5] Wu YL, Putcha N, Ng KW, Leong DT, Lim CT, Loo SCJ, et al. Biophysical responses upon the interaction of nanomaterials with cellular interfaces. *Accounts of Chemical Research*. 2013;**46**(3):782-791
- [6] Borm P, Castranova V. Toxicology of Nanomaterials: Permanent interactive learning. *Particle and Fibre Toxicology*. 2009;**6**:28
- [7] Fan AM, Alexeeff G. Nanotechnology and nanomaterials: toxicology, risk assessment, and regulations. *Journal of Nanoscience and Nanotechnology*. 2010;**10**(12):8646-8657
- [8] Duncan R, Gaspar R. Nanomedicine(s) under the microscope. *Molecular Pharmaceutics*. 2011;**8**:2101-2141

- [9] Corbo C, Molinaro R, Parodi A, Toledano Furman NE, Salvatore F, Tasciotti E. The impact of nanoparticle protein corona on cytotoxicity, immunotoxicity and target drug delivery. *Nanomedicine* [Internet]. 2016;**11**(1):81-100. Available from: <http://www.futuremedicine.com/doi/10.2217/nnm.15.188>
- [10] Salvati A, Åberg C, Dawson KA, Monopoli MP, Åberg C, Salvati A, et al. Biomolecular coronas provide the biological identity of nanosized materials. *Nature Nanotechnology*. 2012;**7**(12):779-786
- [11] Tenzer S, Docter D, Kuharev J, Musyanovych A, Fetz V, Hecht R, et al. Rapid formation of plasma protein corona critically affects nanoparticle pathophysiology. *Nature Nanotechnology* [Internet]. 2013;**8**(10):772-781. Available from: <http://www.ncbi.nlm.nih.gov/pubmed/24056901>
- [12] Shannahan JH, Fritz KS, Raghavendra AJ, Podila R, Persaud I, Brown JM. From the cover: Disease-Induced disparities in formation of the nanoparticle-biocorona and the toxicological consequences. *Toxicological Sciences* [Internet]. 2016;**152**(2):406-416. Available from: <http://www.toxsci.oxfordjournals.org/lookup/doi/10.1093/toxsci/kfw097>
- [13] Huang J, Bu L, Xie J, Chen K, Cheng Z, Li X, et al. Effects of nanoparticle size on cellular uptake and liver MRI with polyvinylpyrrolidone-coated iron oxide nanoparticles. *American Chemical Society Nano*. 2010;**4**(12):7151-7160
- [14] Yameen B, Choi W Il, Vilos C, Swami A, Shi J, Farokhzad OC. Insight into nanoparticle cellular uptake and intracellular targeting. *Journal of Controlled Release*. 2014;**190**:485-499
- [15] Jiang W, Kim BYS, Rutka JT, Chan WCW. Nanoparticle-mediated cellular response is size-dependent. *Nature Nanotechnology* [Internet]. 2008;**3**(3):145-150. Available from: <http://www.ncbi.nlm.nih.gov/pubmed/18654486>
- [16] Mirshafiee V, Mahmoudi M, Lou K, Cheng J, Kraft ML. Protein corona significantly reduces active targeting yield. *Chemical Communications (Cambridge)* [Internet]. 2013;**49**(25):2557-2559. Available from: <http://www.pubmedcentral.nih.gov/articlerender.fcgi?artid=3671387&tool=pmcentrez&rendertype=abstract>
- [17] Arvizo RR, Giri K, Moyano D, Miranda OR, Madden B, McCormick DJ, et al. Identifying new therapeutic targets via modulation of protein corona formation by engineered nanoparticles. *PLoS One*. 2012;**7**(3):e33650
- [18] Podila R, Brown JM. Toxicity of engineered nanomaterials: A Physicochemical Perspective. *Journal of Biochemical and Molecular Toxicology*. 2013;**27**(1):50-55
- [19] Shang L, Nienhaus K, Nienhaus GU. Engineered nanoparticles interacting with cells: Size matters. *Journal of Nanobiotechnology*. 2014;**12**(1):5
- [20] Lundqvist M, Stigler J, Elia G, Lynch I, Cedervall T, Dawson KA. Nanoparticle size and surface properties determine the protein corona with possible implications for biological impacts. *Proceedings of the National Academy of Sciences of the United States of America*. 2008;**105**(38):14265-14270

- [21] Lynch I, Salvati A, Dawson KA. Protein-nanoparticle interactions: What does the cell see? *Nature Nanotechnology*. 2009;**4**:546-547
- [22] Podila R, Chen R, Ke PC, Brown JM, Rao AM. Effects of surface functional groups on the formation of nanoparticle-protein corona. *Applied Physics Letters*. 2012;**101**(26):263701
- [23] Shannahan JH, Podila R, Brown JM. A hyperspectral and toxicological analysis of protein corona impact on silver nanoparticle properties, intracellular modifications, and macrophage activation. *International Journal of Nanomedicine*. Dove Medical Press Ltd. 2015;**10**:6509-6520
- [24] Calin MA, Parasca SV, Savastru D, Manea D. Hyperspectral imaging in the medical field: Present and future. *Applied Spectroscopy Reviews*. 2014;**49**(6):435-447
- [25] Mortimer M, Gogos A, Bartolomé N, Kahru A, Bucheli TD, Slaveykova VI. Potential of hyperspectral imaging microscopy for semi-quantitative analysis of nanoparticle uptake by Protozoa. *Environmental Science & Technology*. 2014;**48**(15):8760-8767
- [26] Fairbairn N, Fernandes R, Carter R, Elliot TJ, Kanaras AG, Muskens OL. Single-nanoparticle detection and spectroscopy in cells using a hyperspectral darkfield imaging technique. *Society of Photographic Instrumentation Engineers*. 2013;**1**(1):859501
- [27] Chen Y, Preece JA, Palmer RE. Processing and characterization of gold nanoparticles for use in plasmon probe spectroscopy and microscopy of biosystems. *Annals of the New York Academy of Sciences*. 2008;**1130**:201-206
- [28] Vetten MA, Tlotleng N, Tanner Rascher D, Skepu A, Keter FK, Boodhia K, et al. Label-free in vitro toxicity and uptake assessment of citrate stabilised gold nanoparticles in three cell lines. *Particle and Fibre Toxicology* [Internet]. 2013;**10**(1):50. Available from: <http://www.pubmedcentral.nih.gov/articlerender.fcgi?artid=3853235&tool=pmcentrez&rendertype=abstract>
- [29] Patskovsky S, Bergeron E, Meunier M. Hyperspectral darkfield microscopy of PEGylated gold nanoparticles targeting CD44-expressing cancer cells. *Journal of Biophotonics*. 2015;**8**(1-2):162-167
- [30] Grabinski C, Schlager J, Hussain S. Hyperspectral microscopy for characterization of gold nanoparticles in biological media and cells for toxicity assessment. *Methods in Molecular Biology* [Internet]. 2013;**1025**:167-178. Available from: <http://www.ncbi.nlm.nih.gov/pubmed/23918337>
- [31] Zhang D, Neumann O, Wang H, Yuwono VM, Barhoumi A, Perham M, et al. Gold nanoparticles can induce the formation of protein-based aggregates at physiological pH. *Nano Letters*. 2009;**9**(2):666-671
- [32] Deng ZJ, Liang M, Monteiro M, Toth I, Minchin RF. Nanoparticle-induced unfolding of fibrinogen promotes Mac-1 receptor activation and inflammation. *Nature Nanotechnology* [Internet]. 2011;**6**(1):39-44. Available from: <Go to ISI>://WOS:000285574000011\ <http://dx.doi.org/10.1038/nnano.2010.250>

- [33] Greenfield NJ. Using circular dichroism spectra to estimate protein secondary structure. *Nature Protocols* [Internet]. 2006;**1**(6):2876-2890. Available from: <http://www.nature.com/nprot/journal/v1/n6/abs/nprot.2006.202.html> \n<http://www.nature.com/doi/10.1038/nprot.2006.202>
- [34] Whitmore L, Wallace BA. Protein secondary structure analyses from circular dichroism spectroscopy: Methods and reference databases. *Biopolymers*. 2008;**89**(5):392-400
- [35] Kelly SM, Jess TJ, Price NC. How to study proteins by circular dichroism. *Biochimica et Biophysica Acta – Proteins and Proteomics*. 2005;**1751**:119-139
- [36] Johnson WC Jr. Secondary structure of proteins through circular dichroism spectroscopy. *Annual Review of Biophysics and Biophysical Chemistry*. 1988;**17**(Cd):145-166
- [37] Marcel YL, Kiss RS. Structure-function relationships of apolipoprotein A-I: A flexible protein with dynamic lipid associations. *Current Opinion in Lipidology*. 2003;**14**(2):151-157
- [38] Huang R, Silva RAGD, Jerome WG, Kontush A, Chapman MJ, Curtiss LK, et al. Apolipoprotein A-I structural organization in high-density lipoproteins isolated from human plasma. *Nature Structural & Molecular Biology* [Internet]. Nature Publishing Group. 2011;**18**(4):416-422. Available from: <http://www.nature.com/nsmb/journal/v18/n4/full/nsmb.2028.html?annotation=1>
- [39] Borhani DW, Rogers DP, Engler JA, Brouillette CG. Crystal structure of truncated human apolipoprotein A-I suggests a lipid-bound conformation. *Proceedings of the National Academy of Sciences of the United States of America*. 1997;**94**(23):12291-12296
- [40] Saha K, Moyano DF, Rotello VM. Protein coronas suppress the hemolytic activity of hydrophilic and hydrophobic nanoparticles. *Materials Horizons*. 2014;**2014**(1):102-105
- [41] Lynch I, Dawson KA. Protein-nanoparticle interactions. *Nano Today*. 2008;**3**:40-47
- [42] Raghavendra AJ, Alsaleh N, Brown JM, Podila R. Charge-transfer interactions induce surface dependent conformational changes in apolipoprotein biocorona. *Biointerphases*. 2017;**12**(2):02D402
- [43] Sengupta B, Gregory WE, Zhu J, Dasetty S, Karakaya M, Brown JM, et al. Influence of carbon nanomaterial defects on the formation of protein corona. *RSC Advances* [Internet]. Royal Society of Chemistry; 2015;**5**(100):82395-82402. Available from: <http://dx.doi.org/10.1039/C5RA15007H>
- [44] Roy SC, Paulose M, Grimes CA. The effect of TiO₂ nanotubes in the enhancement of blood clotting for the control of hemorrhage. *Biomaterials*. 2007;**28**(31):4667-4672
- [45] Morrissey JH, Tajkhorshid E, Rienstra CM. Nanoscale studies of protein-membrane interactions in blood clotting. *Journal of Thrombosis and Haemostasis*. 2011;**9**:162-167
- [46] Wang L, Pal AK, Isaacs JA, Bello D, Carrier RL. Nanomaterial induction of oxidative stress in lung epithelial cells and macrophages. *Journal of Nanoparticle Research*. 2014;**16**(9):2591
- [47] Wang B, Wu P, Yokel RA, Grulke EA. Influence of surface charge on lysozyme adsorption to ceria nanoparticles. *Applied Surface Science*. 2012;**258**(14):5332-5341

- [48] Bradley K, Gabriel J-CP, Briman M, Star A, Grüner G. Charge transfer from ammonia physisorbed on nanotubes. *Physical Review Letters*. 2003;**91**(21):218301
- [49] Firme CP, Bandaru PR. Toxicity issues in the application of carbon nanotubes to biological systems. *Nanomedicine: Nanotechnology, Biology, and Medicine*. 2010;**6**:245-256
- [50] Podila R, Vedantam P, Ke PC, Brown JM, Rao AM. Evidence for charge-transfer-induced conformational changes in CNT-Protein corona. *Journal of Physical Chemistry C*. 2012;**116**(41):22098-22103
- [51] Barros EB, Filho AGS, Lemos V, Filho JM, Fagan SB, Herbst MH, et al. Charge transfer effects in acid treated single-wall carbon nanotubes. *Carbon* [Internet]. 2005;**43**(12):2495-2500. Available from: <Go to ISI>://WOS:000232093400007\ <http://linkinghub.elsevier.com/retrieve/pii/S0008622305002599>
- [52] Mallineni SSK, Shannahan J, Raghavendra AJ, Rao AM, Brown JM, Podila R. Biomolecular interactions and biological responses of emerging two-dimensional materials and aromatic amino acid complexes. *ACS Applied Materials & Interfaces*. 2016;**8**(26):16604-16611

IntechOpen

